



Suomussalmen KTK Oy
Kivikatu 5
89600 Suomussalmi

13

SFS-EN 13242:2013
Maa- ja vesirakentamisessa ja tienrakentamisessa
käytettävät sitomattomat ja hydraulisesti sidotut kiviainekset

Peuravaara
Kalliokiviaines

Raekoko	8/16 mm																												
Rakeisuus SFS-EN933-1	G ₀ <table><tr><td>mm</td><td>%</td></tr><tr><td>31,5</td><td>100</td></tr><tr><td>22,4</td><td>100</td></tr><tr><td>16</td><td>93</td></tr><tr><td>11,2</td><td>42</td></tr><tr><td>8</td><td>10</td></tr><tr><td>5,6</td><td>2</td></tr><tr><td>4</td><td>1</td></tr><tr><td>2</td><td>1</td></tr><tr><td>1</td><td>1</td></tr><tr><td>0.5</td><td>1</td></tr><tr><td>0.25</td><td>0</td></tr><tr><td>0.125</td><td>0</td></tr><tr><td>0.063</td><td>0,0</td></tr></table>	mm	%	31,5	100	22,4	100	16	93	11,2	42	8	10	5,6	2	4	1	2	1	1	1	0.5	1	0.25	0	0.125	0	0.063	0,0
mm	%																												
31,5	100																												
22,4	100																												
16	93																												
11,2	42																												
8	10																												
5,6	2																												
4	1																												
2	1																												
1	1																												
0.5	1																												
0.25	0																												
0.125	0																												
0.063	0,0																												
Litteys SFS-EN933-3:97	- 12																												
Kiintotiheys SFS-EN1097-6:00	- 2,69																												
Vedenimeytyminen	-																												
Murtopintaisten rakeiden osuus	-																												
Iskunkestävyyskoe SFS-EN1097-2:98	- 30 LA 30																												
Koostumus	-																												
Jäädytys-sulatuskestävyys	-																												